



# UPM Opalite

Who, what, where, when? UPM Opalite has the answer. This range of papers is especially tailored for directories. With a very low basis weight, UPM Opalite is thin, smooth, and very durable with top-level opacity. Available in multiple brightness levels for heatset, coldset, and rotogravure printing.

## FEATURES

<b>BRIGHTNESS</b>	55–65
<b>FINISHES</b>	Machine finished
<b>WEIGHT</b>	Available in text weights ranging from 17.8–24.6 lbs. on directory (24x36) basis
<b>GRADE</b>	Machine finished specialty

## BENEFITS

- Proven runability for manufacturing success
- Excellent opacity and readability
- Available in multiple brightness levels for different print needs
- Options for heatset, coldset, and rotogravure printing
- Lightweight yet durable

## APPLICATIONS

Advertising materials, catalogs, and directories.



	BASIS WEIGHTS (lbs.)	GSM (g/m <sup>2</sup> )	BRIGHTNESS (GE)	OPACITY (TAPPI)	MILL(S)
<b>HEATSET WEB OFFSET</b>					
UPM Opalite Plus H (25x38/500)	24.3	36	65	83	Kaipola
	25.7	38	65	85	Kaipola
	27	40	65	85	Kaipola
UPM Opalite H	17.8	29	55	78	Kaipola
	19.1	31	59	79	Kaipola
	20.9	34	59	80	Kaipola
	22.1	36	59	81	Kaipola
	23.4	38	60	83	Kaipola
	24.6	40	60	84	Kaipola
<b>COLDSET WEB OFFSET</b>					
UPM Opalite C*	18	29.3	55	78	Kaipola
	20.9	34	59	80	Kaipola
	22.1	36	59	81	Kaipola
	23.4	38	60	83	Kaipola
	24.6	40	60	84	Kaipola
<b>ROTOGRAVURE</b>					
UPM Opalite Plus G (25x38/500)	24.3	36	65	83	Kaipola
	25.7	38	65	84.5	Kaipola
	27	40	65	85	Kaipola
UPM Opalite G	20.9	34	60	80	Kaipola
	22.1	36	60	81	Kaipola

\*Available upon request.

Values are subject to change.



[www.upm.com/na](http://www.upm.com/na)



**North American Headquarters**  
 55 Shuman Boulevard  
 Naperville, IL 60563  
 Tel. (630) 922-2500  
 Fax (630) 922-2504  
[paperinfo@upm.com](mailto:paperinfo@upm.com)



Scan to view or save a digital version.